



HIGH TEMPERATURE FLEXIBLE SILICONE SEALANT HT FLEXSEAL - 300°C

Description - A cartridge applied Silicone based Sealant designed for use where a flexible bond is required together with **high temperature resistance**. This adhesive gives excellent adhesion between most substrates and, because of its high Elasticity, is particularly suited for gap-filling applications and jointing materials of different thermal expansion characteristics & where vibration is a problem.

- **Excellent adhesion to metals, glass, ceramics, polymers etc**
- **Gap filling & resistant to many solvents**
- **Provides a high temperature flexible joint for flues, ducting etc**
- **Resistant to weathering and ageing - can be used externally**
- **Electrical insulator**
- **Wide operating temperature range up to 300°C**

Colour: **Black / White**
Coverage (5mm diam. bead): **15 metres**
Package: **300ml Eurocartridge**
Shelf Life: **12 months**

General Directions for Use – Replacement of Glass in Oven Door

1. If possible remove oven door and place on a flat surface so that surfaces to be bonded are horizontal.
2. Remove any previous bonding or sealing material.
3. **Thoroughly clean all surfaces** to be bonded using a good oven cleaner followed by a strong detergent such as 'Flash' solution – so that all surfaces to be bonded are clean, dry and free from any residual oils & fats.
4. Apply a 3mm bead of Flexseal to replace old sealer.
5. Place second surface in position, press down firmly around the rim of the glass, using hand pressure.
6. Leave for approx. 36 hours until bonded.

The above information is provided purely on an advisory basis and is not designed to create any representation or warranty implied or otherwise of the capability of the Product. It is the user's responsibility to satisfy himself as to the suitability of such information for his own particular use.

Version Date: 26 April, 2001 Print Date: 25 November, 2008

Minco Sampling Techniques UK Ltd,
Tofts Farm Industrial Estate, Brenda Road, Hartlepool, U.K. TS25 2BS.
Tel(+44):01429-273252 Fax(+44):01429-232611 Web: www.mincouk.com www.fortafix.com